



WATER-BASED KNOCKDOWN WALL TEXTURE SPRAY

DESCRIPTION AND USES

Zinsser® Water-Based Knockdown Wall Texture Spray is designed to easily create a Southwestern or knockdown style texture in minutes. Simply spray it on and lightly knock it down with a putty knife. This low-odor, water-based formula creates professional results quickly. Knockdown Wall Texture is easy to apply and easy to clean. It is great for repairs and patches on already textured walls.

FEATURES

- Controlled spray
- Fast dry
- Repairs damaged texture

PRODUCTS

SKU (20 oz.)	Description
202153	Bright White Light Texture
202154	Bright White Heavy Texture

PRODUCT APPLICATION

PAINTING CONDITIONS

Use in a well ventilated area. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from overspray.

SURFACE PREPARATION

Complete any necessary surface repairs. For best results, prime and seal the surface before painting.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

TESTING SPRAY PATTERN

Practice spraying texture onto cardboard or scrap drywall to determine the best distance and pressure to deliver the preferred pattern.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 24-36" from surface and begin spraying in a circular or quick sweeping motion that evenly covers the surface. Keep the can in motion while spraying. For a heavier knockdown texture, spray in short bursts to build up thickness. Allow to dry 1-5 minutes before lightly flattening (knocking down) texture using a 6-8" large putty knife. For best results, hold knife nearly parallel to the wall. If necessary, texture can be scraped off when wet and reapplied. Can be topcoated in 1-2 hours. **Do not use near open flame.**

DRY & RECOAT TIMES

Dry times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 1-5 minutes, to handle in 10-15 minutes and can be topcoated 1-2 hours. Allow more time for heavier textures.

CLEAN-UP

After use, turn can upside down and press spray nozzle until the spray mist is clear to prevent clogging. Wipe off tip before storing. Clean-up wet paint with water. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse it in water. Do not stick a pin or other objects into the valve stem.

**TECHNICAL DATA****WATER-BASED KNOCKDOWN WALL TEXTURE SPRAY****PHYSICAL PROPERTIES**

		WATER-BASED KNOCKDOWN WALL TEXTURE SPRAY
Resin Type		Ethylene-vinyl Acetate Copolymer
Pigment Type		Titanium Dioxide, Mica, Limestone, Fuller's Earth, Talc
Solvents		Dimethyl Ether, Water
MIR		0.80 Max
Fill Weight		20 ounces
Recommended Dry Film Thickness (DFT) per Coat		Varies depending on porosity and texture of surface
Practical Coverage at Recommended DFT (assume 15% material loss)		Light Texture covers up to 60 sq.ft./can Heavy Texture covers up to 30 sq.ft./can
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	1-5 minutes
	Handle	10-15 minutes
	Topcoat	1-2 hours
Shelf Life		2 years
Flash Point		-42°F (-41°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.